dozenstampers.nl

Technical Data Sheet

ΡΡΗ 35μ

Characteristics

Good adhesion, suitable for frozen food packaging as long as processed above 5°C. Full-surface and reverse printing possible, but is not recommended.

| Data | | | | | |
|--------------------------------|--|--|--|--|--|
| Adhesion | High initial tack | | | | |
| Sound | Noisy | | | | |
| Warranty | positive printing | 6 months | | | |
| | Bleed diapositive printed / coloured | Due to risk of tearing warranty can not be given | | | |
| Max. width printing | Tape width minus 2 mm | | | | |
| Colours | Clear, white, brown | | | | |
| Number of colours printed | Up to 5 colours and full colour | | | | |
| Core diameter | 76 mm (also possible 3M core diameter 50 mm) | | | | |
| Minimum order (50 mm x 66 mtr) | 4 boxes = 144 rolls | | | | |

| Tape material | Тар | ewidt | h in r | nm. | From ■ in maximum length possible | | | | | | | Max. length | Max. number of colours | Thickness foil | |
|------------------|-----|-------|--------|-----|-----------------------------------|---|----|----|----|-----|-----|----------------|------------------------------|-------------------|-----|
| PPH | - | - | - | 19 | 25 | - | 38 | 50 | 75 | 100 | 150 | | 990 mtr | 5 | 35µ |



ΡΡΗ 35μ

Application

| Technical Data | Unit | |
|---------------------|----------|--|
| Base | | polypropylene film, biaxially oriented |
| Adhesive | | Synthetical Rubber Resin |
| Elongation at break | | 154% |
| Thickness | mm | 57µ ± 10% |
| Adhesion to steel | 5,0 N/cm | ±10% |
| Tensile strenght | 54 N/cm | ± 10% |

Properties

- high tensile strength in longitudinal and cross direction
- high adhesion and holding power
- resistant to diluted acids and alkalies
- heat resistant for short exposure up to about +130° C
- low temperature resistant down to about -30° C after application at room temperature
- easy to unwind
- ecologically beneficial